

University of New Hampshire

University of New Hampshire Scholars' Repository

Division 07 – Thermal and Moisture Protection

Chapter 5 – Technical Construction and
Renovation Standards

1-25-2013

071113 - Bituminous Dampproofing

Stephanie Weatherbee
s.weatherbee@unh.edu

Follow this and additional works at: https://scholars.unh.edu/pdch_5_07

Recommended Citation

Weatherbee, Stephanie, "071113 - Bituminous Dampproofing" (2013). *Division 07 – Thermal and Moisture Protection*. 1.

https://scholars.unh.edu/pdch_5_07/1

This Article is brought to you for free and open access by the Chapter 5 – Technical Construction and Renovation Standards at University of New Hampshire Scholars' Repository. It has been accepted for inclusion in Division 07 – Thermal and Moisture Protection by an authorized administrator of University of New Hampshire Scholars' Repository. For more information, please contact Scholarly.Communication@unh.edu.

SECTION 07 1113 - BITUMINOUS DAMPPROOFING

1.1 SUMMARY

A. This Section includes the following:

1. Cold-applied, emulsified-asphalt dampproofing.

1.2 SUBMITTALS

A. LEED Submittal:

1. Product Data for Credit EQ 4.2: For dampproofing, including printed statement of VOC content.

1.3 COLD-APPLIED, EMULSIFIED-ASPHALT DAMPPROOFING

A. Available Manufacturers:

1. ChemMasters Corp.
2. Degussa Building Systems; Sonneborn Brand Products.
3. Henry Company.
4. Karnak Corporation.
5. Koppers Inc.
6. Meadows, W. R., Inc.

B. Trowel Coats: ASTM D 1227, Type II, Class 1.

C. Fibered Brush and Spray Coats: ASTM D 1227, Type II, Class 1.

D. Brush and Spray Coats: ASTM D 1227, Type III, Class 1.

E. VOC Content: 0.25 lb/gal. (30 g/L) or less.

1.4 MISCELLANEOUS MATERIALS

A. Emulsified-Asphalt Primer: ASTM D 1227, Type III, Class 1, except diluted with water as recommended by manufacturer.

B. Asphalt-Coated Glass Fabric: ASTM D 1668, Type I.

1.5 COLD-APPLIED, EMULSIFIED-ASPHALT DAMPPROOFING

A. On Concrete Foundations: Apply 2 brush or spray coats at not less than 1.5 gal./100 sq. ft. (0.6 L/sq. m) for first coat and 1 gal./100 sq. ft. (0.4 L/sq. m) for second coat, 1

fibered brush or spray coat at not less than 3 gal./100 sq. ft. (1.2 L/sq. m), or 1 trowel coat at not less than 4 gal./100 sq. ft. (1.6 L/sq. m).

- B. On Unexposed Face of Concrete Retaining Walls: Apply 1 brush or spray coat at not less than 1.25 gal./100 sq. ft. (0.5 L/sq. m).
- C. On Unexposed Face of Masonry Retaining Walls: Apply primer and 1 brush or spray coat at not less than 1.25 gal./100 sq. ft. (0.5 L/sq. m).
- D. On Exterior Face of Inner Wythe of Cavity Walls: Apply primer and 1 brush or spray coat at not less than 1 gal./100 sq. ft. (0.4 L/sq. m).

END OF SECTION 07 1113