

University of New Hampshire

University of New Hampshire Scholars' Repository

Division 09 – Finishes

Chapter 5 – Technical Construction and
Renovation Standards

1-23-2013

092300 - Gypsum Plastering

Stephanie Weatherbee
s.weatherbee@unh.edu

Follow this and additional works at: https://scholars.unh.edu/pdch_5_09

Recommended Citation

Weatherbee, Stephanie, "092300 - Gypsum Plastering" (2013). *Division 09 – Finishes*. 1.
https://scholars.unh.edu/pdch_5_09/1

This Article is brought to you for free and open access by the Chapter 5 – Technical Construction and Renovation Standards at University of New Hampshire Scholars' Repository. It has been accepted for inclusion in Division 09 – Finishes by an authorized administrator of University of New Hampshire Scholars' Repository. For more information, please contact Scholarly.Communication@unh.edu.

SECTION 09 2300 - GYPSUM PLASTERING

1.1 SUMMARY

- A. The University prefers to use regional materials within a 500 mile radius of the campus.
- B. Section Includes:
 - 1. Gypsum plasterwork on expanded-metal lath.
- C. General:
 - 1. Soft plaster ceiling shall NOT be used.

1.2 SUBMITTALS

- A. LEED Submittals:
 - 1. Product Data for Credit MR 4.1 and Credit MR 4.2: For products having recycled content, documentation indicating percentages by weight of postconsumer and preconsumer recycled content.
 - a. Include statement indicating costs for each product having recycled content.
 - 2. Product Data for Credit EQ 4.1: For sealants, including printed statement of VOC content.

1.3 QUALITY ASSURANCE

- A. Fire-Resistance Ratings: Where indicated, provide gypsum plaster assemblies identical to those of assemblies tested for fire resistance per ASTM E 119 by a qualified testing agency. Identify products with appropriate markings of applicable testing agency.
 - 1. Indicate design designations from UL's "Fire Resistance Directory" or from the listings of another qualified testing agency.

1.4 EXPANDED-METAL LATH

- A. Manufacturers:
 - 1. Dale/Incor.
 - 2. Fry Reglet Corporation.
 - 3. Dietrich Metal Framing; a Worthington Industries Company.
 - 4. Western Metal Lath and Steel Framing Systems.
 - 5. Phillips Manufacturing Co.

- B. Expanded-Metal Lath: ASTM C 847, cold-rolled carbon-steel sheet, ASTM A 653/A 653M, G60 (Z180), hot-dip galvanized zinc coated.
 - 1. Recycled Content: Provide steel products with average recycled content such that postconsumer recycled content plus one-half of preconsumer recycled content is not less than 25 percent.
 - 2. Paper Backing: Kraft paper factory bonded to back of lath.
 - 3. Diamond-Mesh Lath: Self-furring, 3.4 lb/sq. yd. (1.8 kg/sq. m).

1.5 ACCESSORIES

- A. General: Comply with ASTM C 841 and coordinate depth of trim and accessories with thicknesses and number of plaster coats required.
 - 1. Provide zinc and zinc-coated accessories; G60 (Z180) hot-dip galvanized.

1.6 MISCELLANEOUS MATERIALS

- A. Bonding Compound: ASTM C 631.
- B. Steel Drill Screws: For metal-to-metal fastening, ASTM C 1002 or ASTM C 954, as required by thickness of metal being fastened; with pan head that is suitable for application; in lengths required to achieve penetration through joined materials of no fewer than three exposed threads.
- C. Fasteners for Attaching Metal Lath to Substrates: Complying with ASTM C 841.
- D. Wire: ASTM A 641/A 641M, Class 1 zinc coating, soft temper, not less than 0.0475-inch (1.21-mm) diameter, unless otherwise indicated.
- E. Sound Attenuation Blankets: ASTM C 665, Type I (blankets without membrane facing) produced by combining thermosetting resins with mineral fibers manufactured from glass, slag wool, or rock wool.
 - 1. Fire-Resistance-Rated Assemblies: Comply with mineral-fiber requirements of rated assembly.
 - 2. Recycled Content: Provide blankets with recycled content such that postconsumer recycled content plus one-half of preconsumer recycled content constitutes a minimum of 25 percent by weight.
- F. Acoustical Sealant:
 - 1. Provide sealants that have a VOC content of 250 g/L or less when calculated according to 40 CFR 59, Subpart D (EPA Method 24).

1.7 BASE-COAT PLASTER MATERIALS

- A. Base-Coat Plasters, General: ASTM C 28/C 28M.

1.8 FINISH-COAT PLASTER MATERIALS

- A. Gypsum Gaging Plaster: ASTM C 28/C 28M.
- B. Gypsum Ready-Mixed Finish Plaster: Manufacturer's standard, mill-mixed, gaged, interior finish.
- C. High-Strength Gypsum Gaging Plaster: ASTM C 28/C 28M, with a minimum, average, dry compressive strength of 5000 psi (34 MPa) per ASTM C 472 for a neat mix.
- D. Gypsum Keene's Cement: ASTM C 61/C 61M.
- E. Lime: ASTM C 206, Type N, normal finishing hydrated lime.

1.9 PLASTER MIXES

- A. Mixing: Comply with ASTM C 842 and manufacturer's written instructions for applications indicated.

1.10 INSTALLING EXPANDED-METAL LATH

- A. Expanded-Metal Lath: Install according to ASTM C 841.
 - 1. Partition Framing and Vertical Furring: Install flat diamond-mesh lath.
 - 2. Horizontal Framing: Install flat diamond-mesh lath.
 - 3. On Solid Surfaces, Not Otherwise Furred: Install self-furring, diamond-mesh lath.

1.11 PLASTER APPLICATION

- A. General: Comply with ASTM C 842.

END OF SECTION 09 2300