

University of New Hampshire

## University of New Hampshire Scholars' Repository

---

Division 07 – Thermal and Moisture Protection

Chapter 5 – Technical Construction and  
Renovation Standards

---

1-25-2013

### 071800 - Traffic Coatings

Stephanie Weatherbee  
s.weatherbee@unh.edu

Follow this and additional works at: [https://scholars.unh.edu/pdch\\_5\\_07](https://scholars.unh.edu/pdch_5_07)

---

#### Recommended Citation

Weatherbee, Stephanie, "071800 - Traffic Coatings" (2013). *Division 07 – Thermal and Moisture Protection*. 4.

[https://scholars.unh.edu/pdch\\_5\\_07/4](https://scholars.unh.edu/pdch_5_07/4)

This Article is brought to you for free and open access by the Chapter 5 – Technical Construction and Renovation Standards at University of New Hampshire Scholars' Repository. It has been accepted for inclusion in Division 07 – Thermal and Moisture Protection by an authorized administrator of University of New Hampshire Scholars' Repository. For more information, please contact [Scholarly.Communication@unh.edu](mailto:Scholarly.Communication@unh.edu).

## SECTION 07 1800 – TRAFFIC COATINGS

### 1.1 SUMMARY

#### A. Section Includes:

1. Liquid applied waterproofing system.
  - a. Toilet rooms, housekeeping closets and all floors containing floor drains, except where located on slab on grade.
  - b. Floors (including penetrations) of all mechanical rooms above other areas.

### 1.2 SUBMITTALS

#### A. LEED Submittal:

1. Product Data for Credit EQ 4.2: For interior-applied traffic coatings, including printed statement of VOC content.

### 1.3 MATERIALS

- A. Traffic Coatings: Complying with ASTM C 957.
- B. VOC Content: Provide traffic coatings, for use inside the weatherproofing system, with VOC content of 150 g/L when calculated according to 40 CFR 59, Subpart D (EPA Method 24).

### 1.4 LIQUID APPLIED TRAFFIC COATING

#### A. Products:

1. Dex-O-Tex/Crossfield Products Corp; M-E Flooring Systems.
2. Neogard, Division of Jones-Blair; Peda-Gard FC.
3. Tremco Incorporated, Sealant/Waterproofing Division; 360/251 NF Pedestrian Deck Coating.

#### B. Primer: Urethane.

#### C. Preparatory, Base Coats and Topcoat: Single- or multicomponent, aromatic liquid urethane elastomer.

1. Base Coat: 25 mils min. dry film thickness.
2. Topcoat: 11 mils min. dry film thickness.

#### D. Aggregate: Uniformly graded, washed silicon carbide sand of particle sizes, shape, and minimum hardness recommended by traffic coating manufacturer.

