

1-25-2013

092400 - Portland Cement Plastering

Sandra Hickey
sandra.hickey@unh.edu

Follow this and additional works at: http://scholars.unh.edu/pdch_5_09

Recommended Citation

Hickey, Sandra, "092400 - Portland Cement Plastering" (2013). *Division 09 – Finishes*. 2.
http://scholars.unh.edu/pdch_5_09/2

This Article is brought to you for free and open access by the Chapter 5 – Technical Construction and Renovation Standards at University of New Hampshire Scholars' Repository. It has been accepted for inclusion in Division 09 – Finishes by an authorized administrator of University of New Hampshire Scholars' Repository. For more information, please contact nicole.hentz@unh.edu.

092400 - Portland Cement Plastering

SECTION 09 2400 - PORTLAND CEMENT PLASTERING

1.1 SUMMARY

A. Section Includes:

1. Interior portland cement plasterwork on metal lath, unit masonry and monolithic concrete.

1.2 SUBMITTALS

A. LEED Submittals:

1. Product Data for Credit MR 4.1 and Credit MR 4.2: For products having recycled content, documentation indicating percentages by weight of postconsumer and preconsumer recycled content.
 - a. Include statement indicating costs for each product having recycled content.
2. Product Data for Credit EQ 4.1: For sealants, including printed statement of VOC content.

1.3 QUALITY ASSURANCE

A. Fire-Resistance Ratings: Where indicated, provide portland cement plaster assemblies identical to those of assemblies tested for fire resistance per ASTM E 119 by a qualified testing agency. Identify products with appropriate markings of applicable testing agency.

1. Indicate design designations from UL's "Fire Resistance Directory" or from the listings of another qualified testing agency.

B. Sound-Transmission Characteristics: Where indicated, provide portland cement plaster assemblies identical to those of assemblies tested for STC ratings per ASTM E 90 and classified according to ASTM E 413 by a qualified testing agency.

1.4 METAL LATH

A. Expanded-Metal Lath: ASTM C 847 with ASTM A 653/A 653M, G60 (Z180), hot-dip galvanized zinc coating.

1. Recycled Content: Provide steel products with average recycled content such that postconsumer recycled content plus one-half of preconsumer recycled content is not less than 25 percent.
2. Diamond-Mesh Lath: Self-furring, 3.4 lb/sq. yd. (1.8 kg/sq. m).

- B. Paper Backing: FS UU-B-790, Type I, Grade D, Style 2 vapor-permeable paper or Grade B, Style 1a vapor-retardant paper.
 - 1. Provide paper-backed lath at exterior locations.

1.5 ACCESSORIES

- A. General: Comply with ASTM C 1063 and coordinate depth of trim and accessories with thicknesses and number of plaster coats required.
- B. Metal Accessories: Fabricated from zinc or zinc-coated (galvanized) steel

1.6 MISCELLANEOUS MATERIALS

- A. Fiber for Base Coat: Alkaline-resistant glass or polypropylene fibers, 1/2 inch (13 mm) long, free of contaminants, manufactured for use in portland cement plaster.
- B. Bonding Compound: ASTM C 932.
- C. Steel Drill Screws: For metal-to-metal fastening, ASTM C 1002 or ASTM C 954, as required by thickness of metal being fastened; with pan head that is suitable for application; in lengths required to achieve penetration through joined materials of no fewer than three exposed threads.
- D. Fasteners for Attaching Metal Lath to Substrates: Complying with ASTM C 1063.
- E. Wire: ASTM A 641/A 641M, Class 1 zinc coating, soft temper, not less than 0.0475-inch (1.21-mm) diameter, unless otherwise indicated.
- F. Sound Attenuation Blankets: ASTM C 665, Type I (blankets without membrane facing) produced by combining thermosetting resins with mineral fibers manufactured from glass, slag wool, or rock wool.
 - 1. Fire-Resistance-Rated Assemblies: Comply with mineral-fiber requirements of assembly.
 - 2. Recycled Content: Provide blankets with recycled content such that postconsumer recycled content plus one-half of preconsumer recycled content constitutes a minimum of 25 percent by weight.
- G. Acoustical Sealant: As specified in Chapter 5, Division 07, Section 079200.
 - 1. Provide sealants that have a VOC content of 250 g/L or less when calculated according to 40 CFR 59, Subpart D (EPA Method 24).

1.7 PLASTER MATERIALS

- A. Portland Cement: ASTM C 150, Type I, white.
- B. Lime: ASTM C 206, Type S; or ASTM C 207, Type S.

- C. Acrylic-Based Finish Coatings: Factory-mixed acrylic-emulsion coating systems, formulated with colorfast mineral pigments and fine aggregates; for use over portland cement plaster base coats. Include manufacturer's recommended primers and sealing topcoats for acrylic-based finishes.

1.8 PLASTER MIXES

- A. General: Comply with ASTM C 926 for applications indicated.
 - 1. Fiber Content: Add fiber to base-coat mixes after ingredients have mixed at least two minutes. Comply with fiber manufacturer's written instructions for fiber quantities in mixes, but do not exceed 1 lb of fiber/cu. yd. (0.6 kg of fiber/cu. m) of cementitious materials.
- B. Base-Coat Mixes for Use over Metal Lath: Scratch and brown coats for three-coat plasterwork with portland cement mixes.
- C. Base-Coat Mixes: Single base coats for two-coat plasterwork with portland cement mixes.
- D. Job-Mixed Finish-Coat Mixes with portland cement mixes.
- E. Factory-Prepared Finish-Coat Mixes: For acrylic-based finish coatings, comply with manufacturer's written instructions.

1.9 INSTALLING METAL LATH

- A. Expanded-Metal Lath: Install according to ASTM C 1063.
 - 1. Partition Framing and Vertical Furring: Install flat diamond-mesh lath.
 - 2. Flat-Ceiling and Horizontal Framing: Install flat diamond-mesh lath.
 - 3. On Solid Surfaces, Not Otherwise Furred: Install self-furring, diamond-mesh lath.

1.10 PLASTER APPLICATION

- A. General: Comply with ASTM C 926.

END OF SECTION 09 2400